



# PRODUCT SPECIFICATION

Page :1

Revised edition no : 01

## P-641 BITUMINOUS BLACK SOLUTION

Effective Date: 15-7-2014

### Description:

P-641 is a bituminous based coating solution. It is specially formulated to provide a protective coat for metal & steel surfaces, wood surfaces and concrete, against surface corrosion and destruction due to the influence of moisture rain and smoke. It is also suitable for iron pipes, steel bridge, exterior basement wall as waterproofing material.

### Features

- Flexible uses
- Economical
- Excellent adhesion and outstanding protection

### Specification

Appearance	: Thick liquid
Colour	: Black
Binder Type	: Special modified with used thinner, resin and bitumen
Drying Time	: Touch Dry 2 hrs
Consistency Application	: Ready for brush or roller application
Density	: 1 - 1.1 per Ltr
Recoating time	: 1 hour
Thinning	: Turpentine or thinner
Coverage	: Approximately 6 -10 sq m per ltr
Flash point	: Below 80°C
Physical Hazard	: Flammable liquid UN1263 Class 3

### Application

Stir thoroughly before use. All surface to be painted must be clean, dry and free from oil and grease apply at the rate of 10 sq. meter per litre. (If applied onto rough surface, it may require extra)  
Use turpentine or normal thinner to thinning or cleaning tool.

### Safety Handling and Storage

Highly flammable, keep away from fire and sparks. Keep containers tightly closed when not in use.  
Do not smoke when using this product.

### Packing

5 Ltrs, 18 Ltrs and 200 Ltrs

### Note

All recommendations for use of our products, whether given by us in writing, orally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge at the time such recommendations are made. As additional information is learned, these recommendations may be updated. They may also be impacted by circumstances outside our control. Notwithstanding any such recommendations, the user shall remain responsible for satisfying himself that the product as supplied by us are suitable or his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot responsibility therefore. The user shall ensure that the intended use of the products will not infringe any third party's intellectual property rights.

---

#### TLC-KOYA CHEMICALS MANUFACTURING SDN BHD

No.22 & 23, Jalan Maju 1, Cemerlang Industrial Estate, 81800 Ulu Tiram, Johor, Malaysia.

Tel: 607-8675798 Fax: 607-8675799

Website: [www.koyachemicals.com](http://www.koyachemicals.com) EMAIL: [admin@koyachemicals.com](mailto:admin@koyachemicals.com)