



PRODUCT SPECIFICATION	Page :2
	Revised edition no : 02
P-806 SBR BONDING AGENT	Effective Date: 19-7-2014

APPLICATION PROCEDURE 施工程序	SUBSTRATE 基面	TYPE OF WORK & COATING THICKNESS 施作工程及涂敷厚度	MIX PROPORTION 混合规格	CURING PERIOD 固化时间	COVERAGE 用量 m ² /kg
(1) Surface preparation 表面准备工作	The surface must be sound, thoroughly free from oil, grease, tar and other contaminants. Clean the surface of the substrate with a brush to remove any laitance and brittle surface layer. Wash off with water, let it dry before proceeding with the application. 基面必须稳固, 不含任何油脂, 污渍, 沥青等。用铁丝刷清除基面上的浮灰及易碎的表皮, 然后用清水清洗干净。待风干后方可进行下一步的工程。				
(2) Primer 底层涂敷	<u>Wall:</u> 墙壁: Concrete 混凝土 Bricks 砖 Blocks 砌块砖 <u>Floor:</u> 地面: Concrete 混凝土 PC panel 预制混凝土板		P-634 : Water 1 : 2	1 - 5 hrs 一至五小时	15-20
(3) Mortar Finish 砂浆混合式	<u>Wall:</u> 墙壁: Concrete 混凝土 Bricks 砖 Blocks 砌块砖	First coat 第一涂层 (5-6 mm)	Cement : Sand (≤2.5mm) + P-634 : Water 洋灰 : 砂 : 水 5 : 10 + 1 : 2	> 4 days > 四日	1.8
		Finish Coat 面涂层	Cement : Sand 洋灰 : 砂 1 : 3		
	Concrete Floor 混凝土地面	Cement paste (apply with brush) 塑状砂浆 (用漆扫施工)	Cement : Sand (≤0.6mm) + P-634 : Water 洋灰 : 砂 : 水 5 : 5 + 1 : 1	Green on Green 可直接涂 抹在新浇 砂浆土	4.9
		Finish Coat 面涂层	Cement : Sand 洋灰 : 砂 1 : 3		
(4) Tile Finish 瓷砖装璜	<u>Wall:</u> 墙壁: Concrete 混凝土 Bricks 砖 Blocks 砌块砖 <u>Floor:</u> 地面: Concrete 混凝土	First coat(Mortar Setting Bed) 第一涂层(砂浆垫层) (5 - 6 mm)	Cement : Sand (≤2.5mm) + P-634 : Water 洋灰 : 砂 : 水 5 : 10 + 1 : 2	>4 days sprinkle water daily >四天 每日喷 洒水	1.8
		Second Coat 第二涂层 (14 - 15 mm)	Cement : Sand 洋灰 : 砂 1 : 3		
	Tiling(Thin Coat Finish) 瓷砖铺设(薄面涂层) (3 mm)	Tile Adhesive Cement + P-634 : Water 瓷砖黏合剂 : 水 12 + 1 : 2	24 hrs 二十四小时	4	
(5) Cement Filling Compound For surface preparation 基面填补混合式	Horizontal & vertical concrete, PC Panel Monolithic floor finish 横竖混凝土面, 预制混凝土板, 整体式地面层。	Thin Coating 薄涂层 (3 - 4 mm)	Cement : Sand (≤1.2mm) + P-634 : Water 洋灰 : 砂 : 水 5 : 5 - 7.5 + 1 : 2	>4 days sprinkle water daily	2.9
		Pressure Coating 加压涂层 (1 - 2 mm)	Tile Adhesive Cement + P-634 : Water 瓷砖黏合剂 : 水 12 + 1 : 2	> 四天 每日喷 洒水	10 (1 mm)
		Repair finish pressure coating 修补加压面涂层 (1 - 2 mm)	Tile Adhesive Cement + P-634 : Water 瓷砖黏合剂 : 水 12 + 1 : 2	24 hrs 二十四小时	5 (2 mm)

TLC-KOYA CHEMICALS MANUFACTURING SDN BHD

No.22 & 23, Jalan Maju 1, Cemerlang Industrial Estate, 81800 Ulu Tiram, Johor, Malaysia.

Tel: 607-8675798 Fax: 607-8675799

Website: www.koyachemicals.com EMAIL: admin@koyachemicals.com