



# PRODUCT SPECIFICATION

Page :1

Revised edition no : 01

## P-821 ROOFING & AWNING SEALANT

Effective Date: 16-7-2014

### Description:

**P-821** awning is a one part sealant that offer excellent adhesion, outstanding durability and gunnability special for joint sealing in external wall, window, roofs and door frames.

### Features

- \* Excellent adhesion.
- \* Excellent gunnability
- \* Outstanding durability
- \* Flexible
- \* Weather proof
- \* No Sagging
- \* Low Shrinkage

### Specification

Appearance	: Non-Sagging Paste
Odour	: Mild vegetable oil
Specific Gravity	: 1.6 +/- 0.2
Joint Movement	: +/- 3%
Shrinkage	: 5% max.

### Application

- \* Application temperature 5°C to 50°C.
- \* Surface to be applied must be clean and dry.
- \* Cut cartridge nozzle to desired size.
- \* Insert cartridge into Caulking Gun
- \* Push sealant ahead for uniform bead
- \* Tool within 10 minutes
- \* Clean off excess sealant with Mineral Spirit

### Curing Time

P-821 Awning Sealant will tack free in approximately 20 hours.

### Packing & Colour

Packing	: 300 kgs drum and 400 ml cartridge
Colour	: White, Grey and Black
Shelf life	: 24 months

### Note

All recommendations for use of our products, whether given by us in writing, orally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge at the time such recommendations are made. As additional information is learned, these recommendations may be updated. They may also be impacted by circumstances outside our control. Notwithstanding any such recommendations, the user shall remain responsible for satisfying himself that the product as supplied by us are suitable or his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot responsibility therefore. The user shall ensure that the intended use of the products will not infringe any third party's intellectual property rights.

---

#### **TLC-KOYA CHEMICALS MANUFACTURING SDN BHD**

No.22 & 23, Jalan Maju 1, Cemerlang Industrial Estate, 81800 Ulu Tiram, Johor, Malaysia.

Tel: 607-8675798 Fax: 607-8675799

Website: [www.koyachemicals.com](http://www.koyachemicals.com) EMAIL: [admin@koyachemicals.com](mailto:admin@koyachemicals.com)